

Cosentino Industrial, S.A.U.  
Product Department

## LIGHT REFLECTANCE VALUE | LRV - SILESTONE®

In order to be able to determine the LRV of Silestone®, although the test is difficult to carry out on some colours due to their design, the following colours have been selected to cover the whole range of different colours and finishes.

The following results correspond to test reports 092975-006.2; 092975-007.2; 092975-008.2; 092975-009.2; 092975-010.2; 092975-011.2; 092975-012.2; 092975-013.2 y 092975-014.2 carried out in Tecnalía Laboratory.

COLOUR	SERIES	FINISH	AVERAGE LRV
ARCILLA RED	SUNLIT DAYS	SLE	18.72
CORAL CLAY	BASIQ	POL	32.42
DESERT SILVER	ETERNAL	POL - SLE	57.64
ETERNAL MARFIL	ETERNAL	POL - SLE	68.15
ICONIC BLACK	ICONIC	PNB	4.71
ICONIC WHITE	ICONIC	PNB	81.91
KENSHO	ZEN	POL - VOL	33.87
MARENGO	BASIQ	PNB	10.36
ROUGUI	BASIQ	POL - SLE	35.46

For your information, we indicate in the following table the accepted values of LRV to obtain LEED points:

LRV ACCEPTANCE			
CEILING	WALLS	FLOOR	FURNITURE
≥ 85 %	≥ 60 %	≥ 25 %	≥ 45 %

Signed by:



Cristina Guerra  
Certification Manager  
Product Department